


Manufacturer address	KLINGER GmbH, Richard Klinger Str. 37, 65510 Idstein, DE	According to DIN EN 13555 2005-2
Product name	KLINGER® Graphite Laminate SLS150B	
Product dimensions	92 x 49 x 1.5 mm (DIN EN 1514-1 1997-8)	

Minimum stress to seal $Q_{min(L)}$ (at assembly), $Q_{smin(L)}$ (after off-loading) for $p = 10$ bar ($T = 23 \pm 2$ °C)

L [mg/(s·m)]	$Q_{min(L)}$ [MPa]	$Q_{smin(L)}$ [MPa]									
		$Q_A = 5$ [MPa]	$Q_A = 10$ [MPa]	$Q_A = 20$ [MPa]	$Q_A = 40$ [MPa]	$Q_A = 60$ [MPa]	$Q_A = 80$ [MPa]	$Q_A = 100$ [MPa]	$Q_A = 120$ [MPa]	$Q_A = 140$ [MPa]	$Q_A = 160$ [MPa]
1E-0	5		5	5	5	5	5	5			5
1E-1	5		5	5	5	5	5	5			5
1E-2	12			5	5	5	5	5			5
1E-3	45					17	6	5			5
1E-4	83							41			7
1E-5											
1E-6											
1E-7											
1E-8											


Leakage - 23 ± 2 °C / 10 bar



Minimum stress to seal $Q_{min(L)}$ (at assembly), $Q_{smin(L)}$ (after off-loading) for $p = 40$ bar ($T = 23 \pm 2$ °C)

L [mg/(s·m)]	$Q_{min(L)}$ [MPa]	$Q_{smin(L)}$ [MPa]									
		$Q_A = 10$ [MPa]	$Q_A = 20$ [MPa]	$Q_A = 40$ [MPa]	$Q_A = 60$ [MPa]	$Q_A = 80$ [MPa]	$Q_A = 100$ [MPa]	$Q_A = 120$ [MPa]	$Q_A = 140$ [MPa]	$Q_A = 160$ [MPa]	
1E-0	10		10	10	10	10	10	10			10
1E-1	10		10	10	10	10	10	10			10
1E-2	36			26	10	10	10	10			10
1E-3	70					49	21	10			10
1E-4	88							66			17
1E-5											
1E-6											
1E-7											
1E-8											

Leakage - 23 ± 2 °C / 40 bar



Note: the content of darkened cells was not determined respectively is unnecessary

Rev.-No.: 1

Creation date of this sheet: 2012-03-28

Manufacturer address	KLINGER GmbH, Richard Klinger Str. 37, 65510 Idstein, DE	According to DIN EN 13555 2005-2
Product name	KLINGER® Graphite Laminate SLS150B	
Product dimensions	92 x 49 x 1.5 mm (DIN EN 1514-1 1997-8)	

Relaxation ratio P_{QR} for stiffness $C = 500$ [kN/mm]										
Gasket stress	23 ± 2 °C		Temperature 1 [150 °C]		Temperature 2 [300 °C]		P_{QR}	Δe_{Gc} [µm]	P_{QR}	Δe_{Gc} [µm]
	P_{QR}	Δe_{Gc} [µm]	P_{QR}	Δe_{Gc} [µm]	P_{QR}	Δe_{Gc} [µm]				
Stress level 1 [30 MPa]	0.98	6	0.94	16	0.90	25				
Stress level 2 [50 MPa]	0.99	4	0.97	15	0.95	23				
P_{QR} and Δe_{Gc} at maximum gasket stress to be applied Q_{Smax}										
P_{QR} at Q_{Smax}	1.00	0	0.98	30	0.97	45				
Q_{Smax}	200 MPa		180 MPa		180 MPa					

Sekant unloading modulus of the gasket E_G [MPa] and gasket thickness e_G [mm]										
Gasket stress [MPa]	23 ± 2 °C		Temperature 1 [150 °C]		Temperature 2 [300 °C]		E_G [MPa]	e_G [mm]	E_G [MPa]	e_G [mm]
	E_G [MPa]	e_G [mm]	E_G [MPa]	e_G [mm]	E_G [MPa]	e_G [mm]				
0	0	1.530	0	1.530	0	1.530				
1	0	1.500	0	1.501	0	1.502				
20	422	0.943	456	0.915	512	0.900				
30	714	0.889	710	0.873	711	0.857				
40	1022	0.855	966	0.840	981	0.826				
50	1395	0.834	1344	0.819	1250	0.804				
60	1826	0.818	1897	0.803	1618	0.788				
80	2477	0.793	2451	0.778	2442	0.764				
100	3199	0.774	3389	0.758	3342	0.746				
120	3666	0.760	4317	0.744	3955	0.731				
140	4704	0.750	5477	0.725	4528	0.720				
160	4697	0.740	5892	0.688	5149	0.710				
180	5716	0.732	6818	0.594	5331	0.700				
200	6483	0.725								

