



Company Address	W. L. Gore & Associates GmbH, Hermann-Oberth-Strasse 22, 85640 Putzbrunn, Germany	According to DIN EN 13555 2014-07
Gasket Type	GORE® GR Sheet Gasketing	
Sealing element dimensions [mm]	92 x 49 x 6	

L [mg/(s*m)]	Q _{min/L} [MPa]	Minimum stress to seal Q _{min/L} (at assembly), Q _{Smin/L} (after off-loading) for p = 10 bar												
		Q _{Smin/L} [MPa]												
		Q _A = 20 MPa	Q _A = 30 MPa	Q _A = 40 MPa	Q _A = 60 MPa	Q _A = 80 MPa								
10 ⁰	10	10	10	10	10	10								
10 ⁻¹	16	10	10	10	10	10								
10 ⁻²	31			10	10	10								
10 ⁻³	43				10	10								
10 ⁻⁴	52					10	10							
10 ⁻⁵	65						10							




L [mg/(s*m)]	Q _{min/L} [MPa]	Minimum stress to seal Q _{min/L} (at assembly), Q _{Smin/L} (after off-loading) for p = 20 bar												
		Q _{Smin/L} [MPa]												
		Q _A = 20 MPa	Q _A = 30 MPa	Q _A = 40 MPa	Q _A = 60 MPa	Q _A = 80 MPa								
10 ⁰	10	10	10	10	10	10								
10 ⁻¹	22		10	10	10	10								
10 ⁻²	36			10	10	10								
10 ⁻³	46				10	10								
10 ⁻⁴	55					10	10							
10 ⁻⁵	75						57							



Note: the content of darkened cells was not determined respectively is unnecessary Rev - No: 3 Creation date of this sheet: 2016-02-02

Company Address	W. L. Gore & Associates GmbH, Hermann-Oberth-Strasse 22, 85640 Putzbrunn, Germany	According to DIN EN 13555 2014-07
Gasket Type	GORE® GR Sheet Gasketing	
Sealing element dimensions [mm]	92 x 49 x 6	

L [mg/(s*m)]	Q _{minL} [MPa]	Minimum stress to seal Q _{minL} (at assembly), Q _{SminL} (after off-loading) for p = 40 bar					Q _{SminL} [MPa]				
		Q _A = 20 MPa	Q _A = 30 MPa	Q _A = 40 MPa	Q _A = 60 MPa	Q _A = 80 MPa					
10 ⁰	14	10	10	10	10	10					
10 ⁻¹	29		23	10	10	10					
10 ⁻²	41				10	10					
10 ⁻³	49				10	10					
10 ⁻⁴	58				10	10					



Note: the content of darkened cells was not determined respectively is unnecessary Rev - No: 3 Creation date of this sheet: 2016-02-02

