

Company Address	FluorTex GmbH, Auf der Groeb 2C, 83064 Raubling, Germany
Gasket Type	multiFlon
Sealing element dimensions [mm]	92 x 49 x 2

L [mg/(s*m)]	Q _{min/L} [MPa]	Minimum stress to seal Q _{min/L} (at assembly), Q _{Smin/L} (after off-loading) for p = 40 bar									
		Q _{Smin/L} [MPa]									
		Q _A = 10 MPa	Q _A = 20 MPa	Q _A = 40 MPa	Q _A = 60 MPa	Q _A = 80 MPa	Q _A = 100 MPa	Q _A = 120 MPa	Q _A = 140 MPa	Q _A = 160 MPa	
10 ⁰	11		5	5	5	5	5			5	
10 ⁻¹	19		16	5	5	5	5			6	
10 ⁻²	27			5	5	5	5			10	
10 ⁻³	35			17	5	5	5			13	
10 ⁻⁴	46				8	5	5			17	
10 ⁻⁵	73					76	31			23	
10 ⁻⁶											
10 ⁻⁷											
10 ⁻⁸											



